

# Digital ABS Plus

Digital ABS Plus™ is designed to simulate standard ABS plastics by combining high-temperature resistance with toughness. Suitable for parts that require PolyJet™ technology's highest possible impact resistance and shock absorption, Digital ABS Plus significantly improves the mechanical performance of parts and prototypes for design verification and functional performance testing.

Get better impact strength with high-temperature resistance, toughness and superior finish.

Digital ABS Plus is ideal for rapid prototyping snap-fit parts for high or low temperature use, functional designs with multi-material versatility and flexibility, molds, manufacturing tools, electrical parts and more.

Mechanical Properties	Test Method	Value
Tensile Strength	D-638-03	55 – 60 MPa (8,000 – 8,700 psi)
Elongation at Break	D-638-05	25 – 40%
Modulus of Elasticity	D-638-04	2,600 – 3,000 MPa (375,000 – 435,000 psi)
Flexural Strength	D-790-03	65 – 75 MPa (9,500 – 11,000 psi)
Flexural Modulus	D-790-04	1,700 – 2,200 MPa (245,000 – 320,000 psi)
HDT, oC @ 0.45MPa	D-648-06	58 – 68 °C (136 – 154 °F)
HDT, oC @ 0.45MPa after thermal post treatment procedure A	D-648-06	82 – 90 °C (180 – 194 °F)
HDT, oC @ 0.45MPa after thermal post treatment procedure B	D-648-06	92 – 95 °C (198 – 203 °F)
HDT, oC @ 1.82MPa	D-648-07	51 – 55 °C (124 – 131 °F)
Izod Notched Impact	D-256-06	90 – 115 J/m (1.69 – 2.15 ft lb/in)
Tg	DMA, E»	47 – 53 °C (117 – 127 °F)
Shore Hardness (D)	Scale D	85 – 87 Scale D
Rockwell Hardness	Scale M	67 – 69 Scale M
Polymerized Density	ASTM D792	1.17 – 1.18 g/cm <sup>3</sup>

# Digital ABS Plus

System Availability	Layer Thickness Capability	Support Structure	Available Colors
Objet260/350/500 Connex3™	Digital Material 2/3 mode: 30 microns (0.0012 in.)	SUP705 (WaterJet removable) SUP706B (soluble)	<ul style="list-style-type: none"> <li>■ Green (RGD515 Plus and RGD535)</li> <li>■ Ivory (RGD515 Plus and RGD531)</li> </ul>
Stratasys J735™, Stratasys J750™	High Mix or High Speed mode: 27 microns (0.0011 in.)  High Quality mode: 14 microns (0.00055 in.)	SUP705 (WaterJet removable) SUP706B* (soluble)	<ul style="list-style-type: none"> <li>■ Green (RGD515 Plus and RGD535)</li> <li>■ Ivory (RGD515 Plus and RGD531)</li> </ul>
Objet1000 Plus™	Digital Material 2 mode: 36 microns (0.0014 in.)	SUP705 (WaterJet removable)	<ul style="list-style-type: none"> <li>■ Green (RGD515 Plus and RGD535)</li> <li>■ Ivory (RGD515 Plus and RGD531)</li> </ul>

\* Not compatible with or HQ mode for Stratasys J750.

## Stratasys Headquarters

7665 Commerce Way,  
Eden Prairie, MN 55344  
+1 800 801 6491 (US Toll Free)  
+1 952 937-3000 (Intl)  
+1 952 937-0070 (Fax)

[stratasys.com](http://stratasys.com)  
ISO 9001:2008 Certified

1 Holtzman St., Science Park,  
PO Box 2496  
Rehovot 76124, Israel  
+972 74 745 4000  
+972 74 745 5000 (Fax)

